

High Purity PP for Capacitor Film

YUHWA POLYPRO 5014L HPT-H

Features
and Uses

Properties

Application	High Purity PP for Capacitor Film			
Features	IOPP, Ultra High Purity, Rough-surface Film			
Uses	Capacitor Film (Roughness)			
Items		Specification	Unit	Test Method
Melt Index		3.8	g/10min.	ASTM D1238
Density		0.9	g/cm³	ASTM D1505
Catalyst residue, Al (XRF)		2~4	ppm	KPIC Method
Catalyst residue, Cl (XRF)		1~3	ppm	KPIC Method
Total Ash Content (XRF)		10~20	ppm	KPIC Method
Isotactic Index		96	%	KPIC Method
Melting Point		162~165	℃	ASTM D3418
Dielectric Constant		2.25	—	KPIC Method
※ Above data are intended to serve as guides only, and are not sales specification limits.				