

General Homo PP for LiBS Seperator

YUHWA POLYPRO S802H

Features
and Uses

Properties

Application	General Homo PP for LiBS Seperator		
Features	Ultra High Purity, High Stiffness, Heat Resistance, Excellent Gas Pocket		
Uses	LiBS of dry process (Automobile Parts, IT Product Parts)		
Items	Specification	Unit	Test Method
Melt Index	2.5	g/10min.	ASTM D1238
Density	0.9	g/cm³	ASTM D1505
Catalyst residue, Al (XRF)	1~3	ppm	KPIC Method
Catalyst residue, Cl (XRF)	0~2	ppm	KPIC Method
Total Ash Content (XRF)	0-10	ppm	KPIC Method
Isotactic Index	98	%	KPIC Method
Melting Point	165~167	℃	ASTM D3418
Tensile Strength at Yield	370	kgf/cm²	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	18,000	kgf/cm²	ASTM D790
Hardness (Rockwell)	111	R Scale	ASTM D785

※ Above data are intended to serve as guides only and are not sales specification limits