

Typical Properties of ZEONOR 1600 Grade

Properties	Measurement methods	Unit	ZEONOR 1600
Specific gravity	ASTM D792	-	1.01
Water absorption	ASTM D570	%	<0.01
Moisture permeability	JIS Z 0280 (300μm)	g/m ² .24hr	-
Light transmittance	ASTM D1003 (3mm)	%	92
Refractive index	ASTM D542		1.53
Glass transition temperature	DSC	°C	163
Heat distortion temperature	ASTM D648 (18.6kgf)	°C	161
Linear expansion coefficient	ASTM D696	cm/cm°C	6×10 ⁻⁵
Melt flow rate	JIS K6719 (280°C21.18N)	7	20
Molding shrinkage	ASTM D955	%	0.3-0.6
Flexural modulus	ASTM D790	MPa	2600
Flexural strength	ASTM D790	MPa	119
Tensile strength	ASTM D638	MPa	73
Tensile modulus	ASTM D638	MPa	2700
Tensile elongation	ASTM D638	%	10
Izod impact strength	ASTM D256	KJ/m ²	3
Dupont impact strength	ASTM D256	J	1
Rockwell hardness	ASTM D785		75
Volume resistivity	ASTM D257	Ωm	>10 ¹⁶
Dielectric strength	ASTM D149	KV/mm	>70
Dielectric constant	ASTM D150 (1MHz)		2.3
Dielectric loss tangent	ASTM D150 (1MHz)		0.0002
Flammability rating	UL-94	Class	94HB
Processability			Injection-molding; Injection-blow molding Extrusion

The information contained here is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Zeon Chemicals L.P. shall not be liable for and the customer assumes all risk and liability of any use or handling of any materials beyond Zeon Chemicals L.P.'s, direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.