



DuPont™ Elvax® 265A

Description

Generic Name	Ethylene Vinyl Acetate
Product Description	DuPont™ Elvax® 265A is an extrudable ethylene–vinyl acetate copolymer resin available in pellet form for use in conventional extrusion equipment designed to process polyethylene resins.

Product Characteristics

Processing Method	▪ Extrusion
Material Status	▪ Commercial: Active
Availability	▪ not yet determined
Composition	▪ 28 %, Vinyl Acetate
Additive	▪ Antioxidant
Features	▪ Copolymer
Uses	▪ not yet determined
Manufacturer / Supplier	▪ DuPont Packaging & Industrial Polymers

Properties

Physical	Nominal Values	Test Method
Density	0.95g/cm ³	ASTM D792 – ISO 1183
Melt Index (190°C/2.16kg)	3g/10 min	ASTM D1238 – ISO 1133
Thermal	Nominal Values	Test Method
Vicat Softening Point	46°C (115°F)	ASTM D1525 – ISO 306
Melting Point	75°C (167°F)	ASTM D3417
Freezing Point	54°C (129°F)	ASTM D3417

Read and understand the Material Safety Data Sheet (MSDS) before using this product

DuPont Worldwide

Asia Pacific

DuPont Singapore PTE Ltd.
1 Maritime Square #07-01
World Trade Centre
Singapore 0409
Telephone 65-273-2244
Fax 65-272-7494

Australia

DuPont (Australia) Ltd.
254 Canterbury Road
Bayswater, Victoria 3153
Australia
Telephone 3-9721-5900
Fax 3-9721-5650

Brazil/South America

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone 5-11-74166-8542 /
8393
Fax 55-11-4166-8720

Canada

DuPont Canada Inc.
P.O. Box 2200, Streetsville
7070 Mississauga, Road
Mississauga, ONT L5M 2H3
Telephone (Canada Only):
800-268-3943 /
905-821 5953
Fax 905-821-5230

Europe

DuPont de Nemours Int'l.
S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone 022-717-51-11
Fax 022-717-55-00

Japan

Mitsui-DuPont
Polychemicals Co., Ltd.
Kasumigaseki Bldg. 24F
3-2-5 Kasumigaseki
Chiyoda-ku, Tokyo 100, Japan
Telephone 813-3580-5531
Fax 813-3592-1540

Mexico/Central America

DuPont, S.A. de C.V.
Homero 206 Anexo Planta Alta
Col. Chapultepec Morales
11570, D.F. Mexico
Telephone 52-55-57-22-1000
Fax 52-55-57-22-1308

United States

DuPont Packaging and
Industrial Polymers
Barley Mill Plaza 26-2122
Lancaster Pike & Route 141
P.O. Box 80026
Wilmington, DE 19880-0026
Telephone 302-774-1161
Toll-free (USA) 800-438-7225
Fax 302-999-4399

<http://www.dupont.com/>
info@dupont.com

Because DuPont cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Users of DuPont products should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties but they should not be used to establish specification limits or used alone as the basis of design.

Disclosure of this information is not a license to operate or a recommendation to infringe a patent of DuPont or others.

Copyright© 1995-2004. E.I. duPont de Nemours and Company. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ™ or ® are trademarks or registered trademarks of E.I. duPont de Nemours and Company or its affiliates.

This preliminary data sheet is effective as of 3/25/2005, and supersedes all previous versions.