

DuPont™ Delrin®

acetal resin

Delrin® 520MP NC010

Delrin® 520MP is a medium viscosity acetal homopolymer containing 20% Teflon® PTFE Micropowder. It is designed for applications requiring low wear and/or friction against steel, itself, and or other plastics.

Property	Test Method	Units	Value
Identification			
Resin Identification	ISO 1043		POM-SD20
Part Marking Code	ISO 11469		>POM-SD20<
Mechanical			
Yield Stress	ISO 527	MPa (kpsi)	53 (7.7)
Yield Strain	ISO 527	%	13
Nominal Strain at Break	ISO 527	%	
50mm/min			15
Tensile Modulus	ISO 527	MPa (kpsi)	2800 (406)
Flexural Modulus	ISO 178	MPa (kpsi)	2700 (390)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²	
-30°C (-22°F)			4
23°C (73°F)			4
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²	70
Thermal			
Deflection Temperature	ISO 75-1/-2	°C (°F)	
0.45MPa			160 (320)
1.80MPa			94 (201)
Melting Temperature	ISO 11357-1/-3	°C (°F)	
10°C/min			178 (352)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

060809/060810

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.



Product Information

Delrin® 520MP NC010

Property	Test Method	Units	Value
Thermal			
CLTE, Parallel	ISO 11359-1/-2	E-4/C (E-4/F)	
-40 - 23°C (-40 - 73°F)			0.9 (0.50)
23 - 55°C (73 - 130°F)			0.99 (0.55)
55 - 100°C (130 - 212°F)	ISO 11359-1/-2	E-4/C (E-4/F)	1.4 (0.78)
CLTE, Normal			
-40 - 23°C (-40 - 73°F)			0.9 (0.50)
23 - 55°C (73 - 130°F)			0.97 (0.54)
55 - 100°C (130 - 212°F)			1.2 (0.67)
Flammability			
Flammability Classification	IEC 60695-11-10		
1.5mm			HB
3.0mm			HB
Temperature Index			
RTI, Electrical	UL 746B	°C	
1.5mm			105
3.0mm			105
RTI, Impact	UL 746B	°C	
1.5mm			85
3.0mm			85
RTI, Strength	UL 746B	°C	
1.5mm			90
3.0mm			90
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1540 (1.54)
Molding Shrinkage	ISO 294-4	%	
Normal, 2.0mm			1.5
Parallel, 2.0mm			1.9

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

060809/060810

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving implantation in the human body.

For other medical applications see "DuPont Medical Caution Statement", H-50102.



Product Information

Delrin® 520MP NC010

Property	Test Method	Units	Value
Processing			
Melt Temperature Range		°C (°F)	210-220 (410-430)
Melt Temperature Optimum		°C (°F)	215 (420)
Mold Temperature Range		°C (°F)	80-100 (175-210)
Mold Temperature Optimum		°C (°F)	90 (195)
Drying Time, Dehumidified Dryer		h	2-4
Drying Temperature		°C (°F)	80 (175)
Processing Moisture Content		%	<0.2
Hold Pressure Range		MPa (kpsi)	80-100 (12-15)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

060809/060810

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.