



热性能	额定值 单位制	测试方法
热变形温度		
0.45 MPa, 未退火	165 °C	ISO 75-2/B
1.8 MPa, 未退火	125 °C	ISO 75-2/A
维卡软化温度	160 °C	ISO 306/B50
熔融温度 ⁴	178 °C	ISO 11357-3
线形热膨胀系数		ISO 11359-2
流动	6.0E-5 cm/cm/°C	
垂直	8.5E-5 cm/cm/°C	
Annealing Time - Optional	30.0 min/mm	
退火温度	160 °C	
电气性能	额定值 单位制	测试方法
表面电阻率	> 1.0E+15 ohms	IEC 62631-3-2
体积电阻率	1.0E+13 ohms·m	IEC 62631-3-1
相对电容率		IEC 62631-2-1
100 Hz	3.90	
1 MHz	3.90	
漏电起痕指数	600 V	IEC 60112
可燃性	额定值 单位制	测试方法
燃烧速率 ⁵ (1.00 mm)	53 mm/min	ISO 3795
UL 阻燃等级		UL 94
1.5 mm	HB	IEC 60695-11-10, -20
3.0 mm	HB	
FMVSS 可燃性	B	FMVSS 302
雾化 - G-value (condensate)	0.50 mg	ISO 6452
注射	额定值 单位制	
干燥温度	80 °C	
干燥时间 - 热风干燥机	2.0 到 4.0 hr	
建议的最大水分含量	0.20 %	
加工 (熔体) 温度	210 到 220 °C	
Melt Temperature, Optimum	215 °C	
模具温度	80 到 100 °C	
Mold Temperature, Optimum	90 °C	
保压	80.0 到 100 MPa	
Drying Recommended	yes	
Hold Pressure Time	8.00 s/mm	




等温应力与应变 (ISO 11403-1)




正切模量对应力 (ISO 11403-1)




Shear Stress vs. Shear Rate (ISO 11403-1)



Specific Volume vs Temperature (ISO 11403-2)



粘度与剪切率 (ISO 11403-2)



备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² UL 黄卡含有 UL 验证的易燃性和电气特性。UL Prospector 持续努力在 Prospector 中将黄卡链接至单个塑料材料，然而此列表可能未包括所有相应链接。重要的是，我们对 Prospector 中找到的这些黄卡和塑料材料之间的关联进行验证。如需完整的黄卡列表，请访问 UL 黄卡搜索。
- ³ 一般属性：这些不能被视为规格。
- ⁴ 10°C/min
- ⁵ FMVSS 302



购买地点

供应商

DuPont Transportation & Industrial
Wilmington, DE USA
电话: 302-999-4592
Web: <http://plastics.dupont.com/>

分销商

Biesterfeld

Biesterfeld is a Pan European distribution company. Contact Biesterfeld for availability of individual products by country.

电话: +49-40-32008-0

Web: <http://www.biesterfeld-plastic.com/>

供货地区: Algeria, Austria, Belgium, Bosnia and Herzegovina, Brazil, Bulgaria, Croatia, Cyprus, Czech Republic, Egypt, France, Germany, Greece, Hungary, Italy, Libyan Arab Jamahiriya, Luxembourg, Mauritania, Morocco, Netherlands, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Switzerland, Tunisia, Turkey

CCC Plastics

电话: 800-465-6917

Web: <https://www.ccc-group.com/>

供货地区: Canada

Distrupol Ltd

Distrupol Ltd is a Pan European distribution company. Contact Distrupol Ltd for availability of individual products by country.

电话: 08452003040

Web: <http://www.distrupol.com/>

供货地区: Denmark, Finland, Ireland, Norway, Sweden, United Kingdom

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

电话: 440-930-3004

Web: <http://polyonedistribution.com/>

供货地区: Global