

DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN

Product Information

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 70G30HSL NC010 is a 30% glass reinforced, heat stabilised nylon 66 resin for injection moulding.

General information	Value	Unit	Test Standard
Resin Identification	PA66-GF30	-	ISO 1043
Part Marking Code	>PA66-GF30<	-	ISO 11469
Rheological properties	dry / cond	Unit	Test Standard
Moulding shrinkage, parallel	0.3 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.1 / -	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	10000 / 7000	MPa	ISO 527-1/-2
Stress at break	200 / 130	MPa	ISO 527-1/-2
Strain at break	3.4 / 5	%	ISO 527-1/-2
Tensile creep modulus			ISO 899-1
1h	* / 6800	MPa	
1000h	* / 5100	MPa	
Charpy impact strength			ISO 179/1eU
23°C	82 / 93	kJ/m²	
-30°C	70 / 73	kJ/m²	
Charpy notched impact strength			ISO 179/1eA
23°C	12 / 16	kJ/m²	
-30°C	10 / 10	kJ/m²	
Izod notched impact strength			ISO 180/1A
23°C	13 / 17	kJ/m²	
-30°C	12 / 10	kJ/m²	
Hardness, Rockwell, M-scale	104 / 88	-	ISO 2039-2
Hardness, Rockwell, R-scale	124 / 117	-	ISO 2039-2
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	80 / 20	°C	ISO 11357-1/-2
Temp. of deflection under load			ISO 75-1/-2
1.8 MPa	248 / *	°C	
0.45 MPa	261 / *	°C	
Coeff. of linear therm. expansion, parallel	22 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	107 / *	E-6/K	ISO 11359-1/-2
RTI, electrical			UL 746B
0.75mm	140 / *	°C	
1.5mm	140 / *	°C	
3mm	140	°C	
RTI, impact			UL 746B
0.75mm	125	°C	
1.5mm	125 / *	°C	
3mm	125	°C	

DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN

RTI, strength			UL 746B
0.75mm	140	°C	
1.5mm	140 / *	°C	
3mm	140	°C	
Flammability	dry / cond	Unit	Test Standard
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *	-	UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
UL recognition	yes / *	-	UL 94
Oxygen index	24 / *	%	ISO 4589-1/-2
Flammability, 3.0mm	HB / *	-	IEC 60695-11-10
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	13	mm/min	ISO 3795 (FMVSS 302)
Electrical properties	dry / cond	Unit	Test Standard
Relative permittivity			IEC 60250
100Hz	4.4 / 10.8	-	
1MHz	4.1 / 4.6	-	
Dissipation factor			IEC 60250
100Hz	70 / 4600	E-4	
1MHz	150 / 650	E-4	
Volume resistivity	>1E13 / 1E9	Ohm*m	IEC 60093
Surface resistivity	* / 1E13	Ohm	IEC 60093
Electric strength	38 / 32	kV/mm	IEC 60243-1
Comparative tracking index	400 / -	-	IEC 60112
Other properties	dry / cond	Unit	Test Standard
Humidity absorption, 2mm	1.9 / *	%	Sim. to ISO 62
Water absorption, 2mm	6 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m³	ISO 1183
VDA Properties	dry / cond	Unit	Test Standard
Emission of organic compounds	6	µgC/g	VDA 277
Odour	4.5	class	VDA 270
Fogging, F-value (refraction)	95 / *	%	ISO 6452
Fogging, G-value (condensate)	0.3 / *	mg	ISO 6452
Injection	dry / cond	Unit	Test Standard
Drying Recommended	yes	-	-
Drying Temperature	80	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.2	%	-
Melt Temperature Optimum	295	°C	-
Min. melt temperature	285	°C	-
Max. melt temperature	305	°C	-
Max. screw tangential speed	0.2 / *	m/s	-
Mold Temperature Optimum	100	°C	-
Min. mould temperature	70	°C	-
Max. mould temperature	120	°C	-
Hold pressure range	50 - 100	MPa	-
Hold pressure time	3	s/mm	-
Ejection temperature	210	°C	-
Characteristics			
Processing	• Injection Moulding		
Special characteristics	• Heat stabilised or stable to heat		
Regional Availability	• Europe	• Near East/Africa	




DuPont™ Zytel® 70G30HSL NC010


NYLON RESIN

Diagrams

Viscosity-shear rate




Shearstress-shear rate



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN


Dynamic Shear modulus-temperature (dry)



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN


Stress-strain (dry)



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN


Secant modulus-strain (dry)



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN

Specific volume-temperature (pvT)



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)
- ✓ Lactic Acid (10% by mass) (23°C)
- ✗ Hydrochloric Acid (36% by mass) (23°C)
- ✗ Nitric Acid (40% by mass) (23°C)
- ✗ Sulfuric Acid (38% by mass) (23°C)
- ✗ Sulfuric Acid (5% by mass) (23°C)
- ✗ Chromic Acid solution (40% by mass) (23°C)

Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

Ketones

- ✓ Acetone (23°C)

Ethers

- ✓ Diethyl ether (23°C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ SAE 10W40 multigrade motor oil (130°C)
- ✓ SAE 80/90 hypoid-gear oil (130°C)
- ✓ Insulating Oil (23°C)

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5 (60°C)
- ✓ ISO 1817 Liquid 2 - M15E4 (60°C)
- ✓ ISO 1817 Liquid 3 - M3E7 (60°C)
- ✓ ISO 1817 Liquid 4 - M15 (60°C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)



DuPont™ Zytel® 70G30HSL NC010

NYLON RESIN

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✗ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✗ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✓ DOT No. 4 Brake fluid (130°C)
- ✓ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✓ Water (90°C)
- ✗ Phenol solution (5% by mass) (23°C)
- ✗ Coolant Glysantin G48, 1:1 in water (125°C)

Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).



✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

