
# **DuPont Packaging & Industrial Polymers**





# Elvaloy® AC resins Product Data Sheet

		n		

Product Description Elvaloy® AC 34035 is a copolymer of ethylene and butyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process

polyethylene type resins.

Restrictions

Material Status 

• Commercial: Active

Typical Characteristics

Composition 35% By Weight Butyl Acrylate

Features Contains Slip additive.

**Typical Properties** 

Physical Nominal Values Test Method(s)

Density () 0.93 g/cm<sup>3</sup> ASTM D792 ISO 1183

Thermal Nominal Values Test Method(s)

Melting Point (DSC) 90°C (194°F) ASTM D3418 ISO 3146

# **Processing Information**

Fourth Zone

Melt Flow Rate (190°C/2.16kg)

#### General

Maximum Processing Temperature 310°C (590°F)

General Processing Information Elvaloy® AC 34035 is normally processed at melt temperatures ranging from 160°C

- 235°C (320°F - 455°F) in extrusion coating or cast film equipment. A typical extrusion coating extruder temperature profile is given below. Actual processing temperatures will be determined by either the specific equipment or one of the other polymers in a coextrusion. Elvaloy® AC 34035 can also be used in cast extrusions and coextrusions. It is easily processed on standard equipment used for low density

**ASTM D1238** 

ISO 1133

polyethylene.

210°C (410°F)

40 g/10 min

Extrusion Coating/Lamination Processing	Nominal Values
Extrusion Processing Information	A suggested extruder set temperature profile.
Feed Zone	135°C (275°F)
Second Zone	160°C (320°F)
Third Zone	185°C (365°F)

 Fifth Zone
 210°C (410°F)

 Adapter Zone
 210°C (410°F)

 Die Zone
 210°C (410°F)

#### **FDA Status Information**

Elvaloy® AC 34035 resin complies with the U.S. Food and Drug Administration regulation 21CFR175.105; Adhesives, for use as a component of articles intended for use in contact with food. These resins must be separated from contact with food by a suitable functional barrier, and the quantity of adhesive which contacts fatty and aqueous foods shall not exceed the trace amount at seams and edges. This resin also complies with U.S. Food and Drug Administration regulation 21CFR176.180; Components of paper and paperboard in contact with dry food, for use as a component of the uncoated or coated food-contact surface of paper and paperboard in contact with dry food (food type VIII, identified in 21CFR176.170(c), Table 1).

#### Regulatory Information

For information on regulatory compliance outside of the U.S., consult your local DuPont representative.

#### Safety & Handling

Elvaloy® AC resins as supplied by DuPont are not considered hazardous materials. As with any hot material, care should be taken to protect the hands and other exposed parts of the body when handling molten polymer. At recommended processing temperatures, small amounts of fumes may evolve from the resins. When resins are overheated, more extensive decomposition may occur. Adequate ventilation should be provided to remove fumes from the work area. Disposal of scrap presents no special problems and can be by landfill or incineration in a properly operated incinerator. Disposal should comply with local, state, and federal regulations. Resin pellets can be a slipping hazard. Loose pellets should be swept up promptly to prevent falls. For more detailed information on the safe handling and disposal of DuPont resins, a Material Safety Data Sheet can be obtained from the DuPont Packaging and Industrial Polymers website or by contacting your sales representative.

## Read and Understand the Material Safety Data Sheet (MSDS) before using this product

### **Regional Centres**

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

#### **Americas**

DuPont Company, BMP26-2363 Lancaster Pike & Route 141 Wilmington, DE 19805 U.S.A. Telephone +1 302-774-1161 Toll-free (USA) 800-628-6208 Fax +1 302-999-4399

DuPont do Brasil, S.A. Alameda Itapecuru, 506 06454-080 Barueri, SP Brasil Telephone +55 11 4166 8122 Fax +55 11 4166 8720

#### **Asia Pacific**

DuPont China Holding Co., Ltd. Shanghai Branch 399 Keyuan Road, Bldg. 11 Zhangjiang Hi-Tech Park Pudong New District, Shanghai P.R. China (Postcode: 201203) Telephone +86 21 3862 2888 Fax +86-21-3862-2889

#### **Europe / Middle East / Africa**

DuPont de Nemours Int'1. S.A. 2,Chemin du Pavillon Box 50 CH-1218 Le Grand Saconnex Geneva, Switzerland Telephone +41 22 717 51 11 Fax +41 22 717 55 00

http://elvaloy.dupont.com

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medicalk applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont $^{TM}$ , The miracles of science $^{TM}$ , and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 05/05/2009 11:21:57 AM and supersedes all previous versions.