

Multiflex® D1047 BK0200 13718 PL21834 Thermoplastic Elastomer

FEATURES & BENEFITS

- Black

APPLICATIONS

- Multiflex® D1047 BK0200 13718 PL21834 is designed for injected molded, paintable airbag covers and inflatable-restraint components

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test*	Property	Unit	Result
ISO 868	Hardness	Sh.A	46
ISO 1183/A	Density	g/cm ³	0.89
ISO 1133	MVR (2.16 kg/230°C)	cm ³ /10 mn	7.5
MDA 179	Spiral flow condition A	cm	37
ISO 178	Flexural modulus 3 points	MPa	560
ISO 180	Notched Izod Impact at -30°C	KJ/m ²	21
ISO 527-1/H2/500	Tensile strength at break	MPa	18.5
ISO 527-1/H2/500	Elongation at break	%	135
ISO 34	Tear strength	kN/m	120
ISO 527-1/H2/500	Tensile strength at break at -30°C	MPa	30
ISO 527-1/H2/500	Elongation at break at -30°C	%	22
ISO 178	Flexural modulus 3 points at 85°C	MPa	154
ISO 34	Tear strength at 85°C	kN/m	79
ISO 294.4	Shrinkage flow direction at 23°C	%	0.8

*ISO: International Standardization Organization

MDA (Méthode d'Analyse): Issued from ISO Standards

GUIDELINES FOR INJECTION MOLDING

Drying: Multiflex® D1047 BK0200 13718 PL21834 is not moisture sensitive, therefore drying is not needed. However, if this material is stored in high humidity conditions, it is recommended to dry for two hours at maximum 80°C.

Barrel temperature °C ¹	Feed Zone	200°C +/- 20°C
	Zone 1	210°C +/- 20°C
	Zone 2	220°C +/- 20°C
	Nozzle	225°C +/- 20°C
Back Pressure Bars		10 +/- 5
Injection Speed		medium
Holding Pressure		as low as possible
Mold Temperature °C		30–40°C (fixed part) - 20°C (moving part) ²

¹Decrease to 180–200°C in case of aspect issues for 2K airbags.

²Lower T° on moving part is better for easier injection.

**HANDLING
PRECAUTIONS
PRODUCT SAFETY
INFORMATION REQUIRED FOR
SAFE USE IS NOT INCLUDED IN
THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND SAFETY DATA SHEETS
AND CONTAINER LABELS FOR
SAFE USE, PHYSICAL AND
HEALTH HAZARD
INFORMATION. THE SAFETY
DATA SHEET IS AVAILABLE ON
THE DOW CORNING WEBSITE**

USABLE LIFE AND STORAGE

Refer to product label for storage temperature conditions. Containers should be kept tightly closed and kept in cold storage at all times to extend shelf life. Shelf life is indicated by the "Use Before" date found on the product label.

PACKAGING INFORMATION

This product is available in a variety of container sizes. Contact your local Dow Corning sales representative for information about container sizes available in your area.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

**TO THE FULLEST EXTENT
PERMITTED BY APPLICABLE
LAW, DOW CORNING
SPECIFICALLY DISCLAIMS
ANY OTHER EXPRESS OR
IMPLIED WARRANTY OF
FITNESS FOR A PARTICULAR
PURPOSE OR
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

We help you invent the future.™

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.



Multibase is a subsidiary of The Dow Chemical Company.