



## Multiflex<sup>®</sup> TES A5013 TAZ1 TRANS Thermoplastic Elastomer

### FEATURES & BENEFITS

- Soft touch
- Very high flow
- Easy to color
- Transparent
- Compatibility: PP/PE

### APPLICATIONS

- Multiflex<sup>®</sup> TES A5013 TAZ1 TRANS is designed for use in injection molding

### TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

| Test*                           | Property                                               | Unit              | Result |
|---------------------------------|--------------------------------------------------------|-------------------|--------|
| ISO 868                         | Hardness                                               | Sh.A              | 50     |
| ISO 1183/A                      | Density                                                | g/cm <sup>3</sup> | 0.88   |
| MDA 179                         | Spiral flow condition C                                | cm                | > 85   |
| MDA 179                         | Spiral flow condition D                                | cm                | 70     |
| ISO 37 Type 1<br>v = 500 mm/min | Tensile strength at 100% elongation<br>cross direction | MPa               | 1.8    |
| ISO 37 Type 1<br>v = 500 mm/min | Tensile strength at break cross<br>direction           | MPa               | 3.3    |
| ISO 37 Type 1<br>v = 500 mm/min | Elongation at break cross direction                    | %                 | 470    |
| ISO 34                          | Tear strength cross direction                          | kN/m              | 22     |
| MDA 129                         | Compression set 24h/23°C without<br>annealing          | %                 | 31     |

\*ISO: International Standardization Organization

MDA (Méthode d'Analyse): Issued from ISO Standards

### GUIDELINES FOR INJECTION MOLDING

**Drying:** Multiflex<sup>®</sup> TES A5013 TAZ1 TRANS is not moisture sensitive, therefore drying is not needed. However, if this material is stored in high humidity conditions, it is recommended to dry for two hours at maximum 80°C.

|                       |            |                                      |
|-----------------------|------------|--------------------------------------|
| Barrel temperature °C | Feed Zone  | 150 +/- 10                           |
|                       | Transition | 170 +/- 10                           |
|                       | Front      | 190 +/- 10                           |
|                       | Nozzle     | 200 +/- 10                           |
| Melt temperature °C   |            | 200 +/- 10                           |
| Back Pressure Bars    |            | 10 +/- 5                             |
| Injection Speed       |            | 70 +/- 10% max                       |
| Holding Pressure      |            | 30 +/- 10% of Max Injection Pressure |
| Mold Temperature °C   |            | 40 +/- 20                            |
| Hot runner °C         |            | 180 +/- 10                           |

## PROCESSING GUIDE

*Multiflex*<sup>®</sup> brand TES TAZ is designed for injected application: easy mold feeding, for single or multiple cavities geometries are possible due to high fluidity. Compatibility with polyolefin enables bi-injected, overmolded (continuous process or cold insert) parts molding.

Please find below some indications to follow to transform the product. This does not replace molder experience, every mold having its own specificity, but this document is useful for initial parameter choice.

### Background

*Multiflex*<sup>®</sup> TES TAZ can be injected between their melting temperatures from 170°C to 220°C. In this temperature range, materials are stable, above, thermal degradation occurs, resulting in yellowing and significant odor emanation. On a general point of view, viscosity of SEBS based material is principally dependent of applied shear, so *Multiflex*<sup>®</sup> TES TAZ must be injected with high injection speed.

*Multiflex*<sup>®</sup> TES TAZ has been designed to enlarge process window, and can be injected at medium speed.

### Pre-drying

As *Multiflex*<sup>®</sup> TES TAZ is not humidity sensitive, Pre-drying is not needed. In case of “incident”, pre-drying at 50°C during 6 hours is recommended.

### Machinery cleaning

High flow thermoplastic must be used, PEHD, PELD or PP.

### Coloring

*Multiflex*<sup>®</sup> TES TAZ is easily colorable by using color masterbatch based on PP, PE or ethylene copolymers (EVA).

### Processing parameters

Screw:

Geometry: standard injection machine, L/D > 20, compression rate 2:1 to 3:1 (if higher, risk of thermal degradation). Screw speed between

100 to 150 rpm ensures through melting of the material without excessive temperature generation. Start with 120 rpm.

### Back pressure


Must be between 7 and 15 bars. This will ensure a uniform melt without severe shear heating.

### Temperatures (°C)

See Figure 1.

- Feed Zone: 150 +/- 10
- Zone 1: 170 +/- 10
- Zone 2: 190 +/- 10
- Nozzle: 200 +/- 10

**Figure 1: Injection molding processing temperatures**



### Injection speed

Injection speed and fill time are highly dependent on part geometry, complexity and gate design. Faster speeds typically result in easier mold filling while lower speeds result in better surface in better surface appearance. High injection speed, around 70% of maximum injection speed should be used initially.

### Holding pressure

Start with a pressure equivalent to 30% of maximum injection pressure. Excessive holding pressure can result in distortion in the area of the gate due to elastomeric characteristics of the material.

### Holding time

Three seconds can be used to start to ensure sufficient time for gate freeze off. Holding time can be slowly reduced until changes in part appearance or weight occur.

### Mold

Use conventional mold design (venting, finish, draft) with temperatures from 10 to 60°C, but typically chosen in the range 40°C +/-20°C gives good results. To

improve the transparency, hot mold is recommended.

### Hot Runners

Apply a temperature of 180°C +/- 10.

### Recycling

*Multiflex*<sup>®</sup> TES TAZ is 100% recyclable without properties loss. We recommend a maximum level of 10% of recycling material in virgin material.

## HANDLING

## PRECAUTIONS

**PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE**

## USABLE LIFE AND STORAGE

Refer to product label for storage temperature conditions. Containers should be kept tightly closed and kept in cold storage at all times to extend shelf life. Shelf life is indicated by the “Use Before” date found on the product label.

## PACKAGING INFORMATION

This product is available in a variety of container sizes. Contact your local Dow Corning sales representative for information about container sizes available in your area.

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## **HEALTH AND ENVIRONMENTAL INFORMATION**

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

## **LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*We help you invent the future.™*



Multibase is a subsidiary of The Dow Chemical Company.