

Product Information Automotive and Transportation



DOW CORNING

Multiflex[®] TES D3502 EU1 NAT 22033 Thermoplastic Elastomer

FEATURES & BENEFITS

- Aesthetics
- Natural color
- Compatibility: PP/PE

APPLICATIONS

- *Multiflex[®]* TES D3502 EU1 NAT 22033 is designed for use in extrusion

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test*	Property	Unit	Result
ISO 868	Hardness	Sh. D	34
ISO R1183	Density		0.89
MDA 179	Spiral flow condition A	cm	35
ISO 1133	MVR (5 kg/230°C)	cm ³ /10 min	10
ISO 178	Flexural modulus 3 points	MPa	200
ISO 527-2/5A/500 NR	Tensile strength at break	MPa	14
ISO 527-2/5A/500 NR	Elongation at break	%	170
ISO 34	Tear strength	kN/m	75

*ISO: International Standardization Organization

MDA (Méthode d'Analyse): Issued from ISO Standards

USABLE LIFE AND STORAGE

Refer to product label for storage temperature conditions. Containers should be kept tightly closed and kept in cold storage at all times to extend shelf life. Shelf life is indicated by the "Use Before" date found on the product label.

PACKAGING INFORMATION

This product is available in a variety of container sizes. Contact your local Dow Corning sales representative for information about container sizes available in your area.

HANDLING PRECAUTIONS PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN

**THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT AND
SAFETY DATA SHEETS AND
CONTAINER LABELS FOR SAFE
USE, PHYSICAL AND HEALTH
HAZARD INFORMATION. THE
SAFETY DATA SHEET IS
AVAILABLE ON THE
DOW CORNING WEBSITE AT**

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.™

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.



Multibase is a subsidiary of The Dow Chemical Company.