

# TPSiV® Thermoplastic Elastomers

Achieve greater aesthetics, design freedom and durability with the benefits of silicone.



**TPSiV® materials offer a combination of properties and benefits from thermoplastics and fully crosslinked silicone rubber.**

## Exceptional Properties

- Unique tactile perception: soft touch and silky feel without the need for additional processing or coating
- Abrasion, scratch, heat and UV resistant
- Chemical resistant, including sweat and oils
- Stain resistant, easy to clean, dirt and dust pick-up resistant
- Prolongated skin contact compliant<sup>(1)</sup>
- Water, beverage and food contact compliant<sup>(1)</sup>
- Available grades from low 50 Shore A to 80 Shore A hardness
- Strong bonding with PC/ABS or any polar substrates

## Application Range

- Ergonomic parts: handles or soft touch grips
- Wearable electronics
- Portable speakers and accessory cases
- Flexible pipe for potable water tubing applications
- Automotive interior parts

## Tough and Versatile

When you combine the strength, toughness, and abrasion resistance of a thermoplastic elastomer with the soft silkiness, UV and chemical resistance, and colorability of silicone, you get DuPont™ TPSiV®. The materials contain no plasticizers that can create surface stickiness. Instead, the silicone itself acts as a softening agent.

As with other TPVs, these thermoplastic compounds are melt processable and fully recyclable. And they can be precisely color-matched to your specification in matte or glossy finishes.

These materials are ready to use TPEs that require no post-treatment. Unlike other thermoplastic vulcanizates, they can be recycled and reused in your manufacturing processes.

## Overmolding Compatibility

Our TPSiV® portfolio is compatible with a range of rigid substrates, and self-adheres to create a strong bond through overmolding or co-molding. They enable the creation of durable, silky surfaces that are ideal for ergonomic applications, wearable tech, and portable electronic devices.

## Advantages



<sup>(1)</sup> Contact our experts for regulatory compliance guidance.

## Performance Properties of TPSiV® Thermoplastic Elastomers

### TPSiV® 4000 series:

UV stable, colorable, TPE with excellent bonding to polycarbonate, ABS, acrylic, nylon, and other polar substrates.

### TPSiV® 4200 series:

Improved chemical and mechanical resistance with excellent bonding to polycarbonate, ABS, acrylic, nylon, and other polar substrates.

### The TPSiV® 5300 series:

Suitable for food and water contact, with superior color resistance to chemicals and excellent bonding to olefinic resins.

Properties	Unit	TPSiV® 4000-50A	TPSiV® 4000-60A	TPSiV® 3345-65A	TPSiV® 4000-75A SR	TPSiV® 4200-70A	TPSiV® 4200-75A SR	TPSiV® 5300 A6002
Hardness ISO 48-4	Shore A	51	62	70	77	73	78	60
Density ISO 1183		1,1	1,1	1,17	1,1	1,18	1,17	0,9
Stress at 100% elongation ISO 527-1/-2 or ISO 37	MPa	1,4	2,2	3,3	3,9	3,9	4,5	1,9
Tensile strength at break ISO 527-1/-2 or ISO 37	MPa	3,4	5,2	7,3	15,8	14,5	24	7,4
Elongation at break ISO 527-1/-2 or ISO 37	%	710	600	560	600	550	650	845
Tear strength ISO34	kN/m	23,7	30	41	64	48	72	44
Taber abrasion ASTM D3389	mg/1000 rev	129	89	95	40	65	26	70
Compression set 22hrs at 22°C ISO 815	%	32,5	33	25	19	22	27	34
<b>Product features</b>								
Minimum service temperature		-30°C	-30°C	-30°C	-30°C	-40°C	-40°C	-30°C
Maximum temperature exposure		120°C	120°C	120°C	120°C	150°C	150°C	130°C
UV resistance		✓✓	✓✓	✓✓	✓✓✓	✓ Black only	✓ Black only	✓✓
Scratch & Abrasion resistance		✓	✓	✓	✓✓✓	✓✓	✓✓✓	✓
Stain resistance (Static & Dynamic)		✓	✓	✓	✓✓	✓	✓	✓✓✓
Skin contact compliant*			✓		✓		✓	
Food contact compliant**								✓
Bonding / chemical compatibility		PC/ABS/ASA	PC/ABS/ASA	PC/ABS/ASA (Nylon optionally)	PC/ABS/ASA (Nylon optionally)	PC/ABS/ASA	PC/ABS/ASA (Nylon optionally)	Polyolefin

Source: DuPont

\*USP chapter <88> and ISO 10993-10:2010

\*\*EU 10/2011\*\*

dupont.com



dupont.com/multibase

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2023 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Form No. 001-20904-HMC0723