

Panlite® B-4110R

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

Carbon fiber reinforced grades-10% Carbon fiber

General

Filler / Reinforcement	• Carbon Fiber, 10% Filler by Weight
Properties	• Creep Resistant • High Rigidity
Uses	• Industrial Applications
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.40 to 0.60	%	
Flow : 4.00 mm	0.10 to 0.30	%	
Water Absorption (24 hr, 23°C)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7700	MPa	ISO 527-1/1
Tensile Stress (Break, 23°C)	105	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2/5
Flexural Modulus ² (23°C)	7500	MPa	ISO 178
Flexural Stress ² (23°C)	160	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	32	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/B
0.45 MPa, Unannealed	148	°C	
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	146	°C	
Vicat Softening Temperature	151	°C	ISO 306/B50
CLTE - Flow	3.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	6.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec (1.5 mm)	80.0	°C	UL 746B
RTI Imp (1.5 mm)	80.0	°C	UL 746B
RTI Str (1.5 mm)	80.0	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+2	ohms	IEC 60093
Volume Resistivity	1.0E+2 to 1.0E+3	ohms·cm	IEC 60093

Panlite® B-4110R

TEIJIN LIMITED - Polycarbonate

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	V-2		UL 94

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	5.0 to 8.0	hr	
Processing (Melt) Temp	270 to 320	°C	
Mold Temperature	80 to 120	°C	

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 2.0 mm/min