

Panlite® G-3310M

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

Glass fiber reinforced grades-10% Glass fiber, Isotropy grade

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Features	• Good Isotropy		
Uses	• Camera Applications	• Industrial Applications	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Water Absorption (24 hr, 23°C)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2/1
Tensile Stress (Break)	55.0	MPa	ISO 527-2/5
Tensile Strain (Break)	60	%	ISO 527-2/5
Flexural Modulus ²	2600	MPa	ISO 178
Flexural Stress ²	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	135	°C	ISO 75-2/B
Heat Deflection Temperature (1.8 MPa, Unannealed)	124	°C	ISO 75-2/A
Vicat Softening Temperature	140	°C	ISO 306/B50
CLTE - Flow	6.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	6.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec (1.5 mm)	130	°C	UL 746
RTI Imp (1.5 mm)	120	°C	UL 746
RTI Str (1.5 mm)	130	°C	UL 746

Panlite® G-3310M

TEIJIN LIMITED - Polycarbonate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength ³	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.20		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	1.0E-3		
1 MHz	9.0E-3		
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	V-2		UL 94

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 2.0 mm/min
- ³ short time test