

# Panlite® GN-3410R

## TEIJIN LIMITED - Polycarbonate

### General Information

#### Product Description

Glass fiber reinforced grades - 10% Glass fiber, Flame resistant grade

#### General

|                        |                                          |                             |                 |
|------------------------|------------------------------------------|-----------------------------|-----------------|
| Material Status        | • Commercial: Active                     |                             |                 |
| Availability           | • Africa & Middle East<br>• Asia Pacific | • Europe<br>• Latin America | • North America |
| Filler / Reinforcement | • Glass Fiber, 10% Filler by Weight      |                             |                 |
| Features               | • Creep Resistant                        | • Flame Retardant           | • High Rigidity |
| Uses                   | • Electrical Parts                       | • Industrial Applications   |                 |
| Forms                  | • Pellets                                |                             |                 |
| Processing Method      | • Injection Molding                      |                             |                 |

### ASTM & ISO Properties <sup>1</sup>

| Physical                                           | Nominal Value | Unit              | Test Method     |
|----------------------------------------------------|---------------|-------------------|-----------------|
| Density                                            | 1.28          | g/cm <sup>3</sup> | ISO 1183        |
| Molding Shrinkage                                  |               |                   | Internal Method |
| Across Flow : 4.00 mm                              | 0.40 to 0.60  | %                 |                 |
| Flow : 4.00 mm                                     | 0.30 to 0.50  | %                 |                 |
| Water Absorption (24 hr, 23°C)                     | 0.16          | %                 | ISO 62          |
| Mechanical                                         | Nominal Value | Unit              | Test Method     |
| Tensile Modulus                                    | 3700          | MPa               | ISO 527-2/1     |
| Tensile Stress (Break)                             | 75.0          | MPa               | ISO 527-2/5     |
| Tensile Strain (Break)                             | 3.5           | %                 | ISO 527-2/5     |
| Flexural Modulus <sup>2</sup>                      | 3600          | MPa               | ISO 178         |
| Flexural Stress <sup>2</sup>                       | 125           | MPa               | ISO 178         |
| Impact                                             | Nominal Value | Unit              | Test Method     |
| Charpy Notched Impact Strength                     | 9.0           | kJ/m <sup>2</sup> | ISO 179         |
| Charpy Unnotched Impact Strength                   | 45            | kJ/m <sup>2</sup> | ISO 179         |
| Thermal                                            | Nominal Value | Unit              | Test Method     |
| Heat Deflection Temperature (0.45 MPa, Unannealed) | 147           | °C                | ISO 75-2/B      |
| Heat Deflection Temperature (1.8 MPa, Unannealed)  | 144           | °C                | ISO 75-2/A      |
| Vicat Softening Temperature                        | 149           | °C                | ISO 306/B50     |
| CLTE - Flow                                        | 4.0E-5        | cm/cm/°C          | ISO 11359-2     |
| CLTE - Transverse                                  | 6.0E-5        | cm/cm/°C          | ISO 11359-2     |
| RTI Elec (1.5 mm)                                  | 130           | °C                | UL 746          |
| RTI Imp (1.5 mm)                                   | 120           | °C                | UL 746          |
| RTI Str (1.5 mm)                                   | 130           | °C                | UL 746          |

Panlite® GN-3410R

TEIJIN LIMITED - Polycarbonate

| Electrical                     | Nominal Value | Unit    | Test Method    |
|--------------------------------|---------------|---------|----------------|
| Surface Resistivity            | > 1.0E+15     | ohms    | IEC 60093      |
| Volume Resistivity             | > 1.0E+15     | ohms·cm | IEC 60093      |
| Electric Strength <sup>3</sup> | 35            | kV/mm   | IEC 60243-1    |
| Relative Permittivity          |               |         | IEC 60250      |
| 100 Hz                         | 3.20          |         |                |
| 1 MHz                          | 3.20          |         |                |
| Dissipation Factor             |               |         | IEC 60250      |
| 100 Hz                         | 1.0E-3        |         |                |
| 1 MHz                          | 9.0E-3        |         |                |
| Comparative Tracking Index     | 175           | V       | IEC 60112      |
| Flammability                   | Nominal Value | Unit    | Test Method    |
| Flame Rating                   |               |         | UL 94          |
| 0.43 mm                        | V-2           |         |                |
| 1.5 mm                         | V-0           |         |                |
| Glow Wire Flammability Index   |               |         | IEC 60695-2-12 |
| 1.0 mm                         | 960           | °C      |                |
| 3.0 mm                         | 960           | °C      |                |
| Glow Wire Ignition Temperature |               |         | IEC 60695-2-13 |
| 1.0 mm                         | 875           | °C      |                |
| 3.0 mm                         | 900           | °C      |                |

Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 mm/min

<sup>3</sup> short time test