

Panlite® GN-3540RI

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

Glass fiber reinforced grades - 40% Glass fiber, Low anisotropy grade, Flame resistant

General

Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Properties	• Creep Resistant • High Rigidity • Flame Retardant • Low Anisotropy
Uses	• Camera Applications • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 2.00 mm	0.050 to 0.20	%	
Flow : 2.00 mm	0.020 to 0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	152	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	1.5	%	ISO 527-2/5
Flexural Modulus ² (23°C)	12000	MPa	ISO 178
Flexural Stress ² (23°C)	211	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	42	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	105	°C	
CLTE - Flow	1.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	4.5E-5	cm/cm/°C	ISO 11359-2
RTI Elec (1.0 mm)	80.0	°C	UL 746B
RTI Imp (1.0 mm)	80.0	°C	UL 746B
RTI Str (1.0 mm)	80.0	°C	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.0 mm	V-1		
1.6 mm	V-0		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	100	°C
Drying Time	5.0 to 8.0	hr

Panlite® GN-3540RI

TEIJIN LIMITED - Polycarbonate

Injection	Nominal Value	Unit
Processing (Melt) Temp	260 to 310	°C
Mold Temperature	70 to 100	°C

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 2.0 mm/min