

Panlite® MN-4400Z

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

Transparent Flame Retardant, Weather resistant

General

Properties	• Bromine Free	• Flame Retardant	• UV Resistant
Uses	• General Purpose	• Lighting Applications	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	69.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	> 50	%	ISO 527-2/50
Flexural Modulus ² (23°C)	2400	MPa	ISO 178
Flexural Stress ² (23°C)	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	125	°C	
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	7.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec (2.0 mm)	80.0	°C	UL 746B
RTI Imp (2.0 mm)	80.0	°C	UL 746B
RTI Str (2.0 mm)	80.0	°C	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.0 mm)	V-0		UL 94
Optical	Nominal Value	Unit	Test Method
Light Transmittance (3000 µm)	88.0	%	ASTM D1003

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	5.0 to 8.0	hr
Processing (Melt) Temp	270 to 320	°C
Mold Temperature	80 to 120	°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min