

Technical Data Sheet

CAPILENE[®] TP 50 AV

Polypropylene Impact Copolymer

Description

CAPILENE[®] TP 50 AV is a very high flow polypropylene heterophasic copolymer intended for injection molding.

CAPILENE[®] TP 50 AV features: excellent impact strength, controlled rheology, very high flow, antistatic additive, excellent processability and low warpage.

Applications

CAPILENE[®] TP 50 AV is suitable for: thin walled items, products with long flow length or complex design.

Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.caol.co.il>

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230°C/2.16Kg)	ISO 1133	50	g/10 min
Mechanical				
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	18	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	8	%
Flexural Modulus	(5 mm/min)	ISO 178	800	MPa
Izod Impact Strength, notched	(+23°C)	ISO 180	40	kJ/m ²
Izod Impact Strength, notched	(-20°C)	ISO 180	8	kJ/m ²
Thermal				
Vicat Softening Temperature	(10 N)	ISO 306	140	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	65	°C

**Typical values; not to be construed as specifications.*