

# Ravaplen® 60 T 44

Polypropylene

Near Prime Compound

## Description:

Near Prime PP Copolymer, light weight talc filled, UV stabilised, suitable for interior applications, coloured upon request

## General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	0,95	g/cm <sup>3</sup>

## Thermal

HDT/A (1,82MPa)	ISO 75A	55	°C
-----------------	---------	----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	6	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	20	MPa
Elongation at yield (23 °C)	ISO 527	6	%
Tensile modulus (23 °C)	ISO 527	1300	MPa
Flexural modulus (23 °C)	ISO 178	1500	MPa

## Various

Ash content (600 °C)	ISO 3451	7	%
----------------------	----------	---	---

## Remark:

PRELIMINARY DATASHEET

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
May 2021