

# **Ravamid® A BK**

Polyamide 66  
Industrial Quality Compound

## **Description:**

Polyamide 66 black containing recycled material, general purpose, also available Heat Stabilized (H) and UV Stabilized (UV)

## **General**

|                                |          |      |                   |
|--------------------------------|----------|------|-------------------|
| Density                        | ISO 1183 | 1.14 | g/cm <sup>3</sup> |
| Mold shrinkage (Parallel)      |          | 1.50 | %                 |
| Mold shrinkage (Perpendicular) |          | 2.0  | %                 |

## **Thermal**

|                                   |         |     |    |
|-----------------------------------|---------|-----|----|
| HDT/A (1,82MPa)                   | ISO 75A | 70  | °C |
| Vicat softening point (B50 (50N)) | ISO 306 | 215 | °C |

## **Mechanical**

|                                     |           |      |                   |
|-------------------------------------|-----------|------|-------------------|
| Izod notched impact strength (23°C) | ISO 180/A | 7    | kJ/m <sup>2</sup> |
| Tensile stress at yield             | ISO 527   | 60   | MPa               |
| Tensile stress at break             | ISO 527   | 57   | MPa               |
| Elongation at break                 | ISO 527   | 40   | %                 |
| Flex modulus                        | ISO 178   | 2100 | MPa               |

## **Flammability**

|                                       |                |     |    |
|---------------------------------------|----------------|-----|----|
| Flammability (3,2mm)                  | UL94           | HB  |    |
| Flammability (1,6mm)                  | UL94           | HB  |    |
| Glow wire flammability index (2,0 mm) | IEC 60695-2-12 | 650 | °C |

## **Various**

|          |         |       |   |
|----------|---------|-------|---|
| Humidity | ISO 960 | ≤0.25 | % |
|----------|---------|-------|---|

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## **Ravago Group Headquarters**

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Jul 2010