

Ravamid® A GF 30 BK SM

Polyamide 66
Industrial Quality Compound

Description:

Polyamide 66 black containing recycled material, 30% glass fibre reinforced, self lubricating grade (sulphide molybdenum modified, low coefficient of friction)

General

Density	ISO 1183	1.35	g/cm ³
Mold shrinkage (Parallel)		0.35	%
Mold shrinkage (Perpendicular)		1.46	%

Thermal

HDT/A (1,82MPa)	ISO 75A	215	°C
Vicat softening point (B50 (50N))	ISO 306	235	°C

Mechanical

Izod notched impact strength (23°C)	ISO 180/A	8	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179/1eA	7	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179/1eU	50	kJ/m ²
Tensile stress at break	ISO 527	145	MPa
Elongation at break	ISO 527	4	%
Tensile modulus	ISO 527	8000	MPa
Flex modulus	ISO 178	7800	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤0.15	%
Coefficient of friction (static)	ASTM D3702	0.45	-
Coefficient of friction (dynamic)	ASTM D3702	0.38	-

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Nov 2010