



Polyamide 6 Industrial Quality Compound

Description:

Polyamide 6 black containing recycled material, impact modified, also available UV Stabilized (UV) and heat stabilized (H)

General

Density Linear mould shrinkage	ISO 1183 ISO 2577	1.08 1,00	g/cm³ %		
Thermal					
HDT/A (1.82MPa)	ISO 75A	50	°C.		

ISO 306

200

Mechanical

Vicat softening point (B50 (50N))

moonamou.			
Izod notched impact strength (23°C)	ISO 180	10.5	kJ/m²
Izod notched impact strength (-30°C)	ISO 180	8	kJ/m²
Charpy notched impact strength (23 °C)	ISO 179	10.5	kJ/m²
Charpy notched impact strength (-30°C)	ISO 179	8	kJ/m²
Tensile stress at yield	ISO 527	55	MPa
Tensile stress at break	ISO 527	45	MPa
Elongation at break	ISO 527	20	%
Flex modulus	ISO 178	2300	МРа

Flammability

Flammability (3,2mm)	UL94	НВ	
Flammability (1,6mm)	UL94	НВ	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

F	Humidity	ISO 960	≤0.25	%
- 1	•			

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

°C