

SCOLEFIN® general purpose

Ravago presents

SCOI FFIN®

SCOLEFIN® PP Compounds is designed with the best combination of PP base polymers and a wide variety of different advanced stabilizations and fillers using unique know-how on compounding technologies.

With Ravago's experience and expertise on plastic solutions, this brand of prime quality materials can serve many different applications independent of colors, specifications and needs.

Wide portfolio of many different characteristics, SCOLEFIN® is the prime PP compound that will fulfill all customers' needs.

Prime SCOLEFIN® PP compounds provide:



Excellent surface finish



Scratch resistance compounds



UV resistance



Optimized mechanical properties



Low odour and fogging



Long term thermal stability



Easy flow



Color matched on request



SCOLEFIN® general purpose - product portfolio

| | | Density | MFI | | | |
|-----------------|--|-------------|------------------------------|--|--|--|
| Grade name | Product description | [g / cm³] | 230° / 2,16 Kg [g / 10min] | | | |
| | | ISO 1183 | ISO 1133 | | | |
| General purpose | | | | | | |
| 53 G 25 | PP copolymer based Glassfibre 30%, medium –high impact /stiffness balance. Natural or Black, UV stabilized for exteriors, building and construction applications | 1,12 | 15 | | | |
| 12 T 20 | PP copolymer,fine white talcum filled, natural and aesthetic extrusion grade. Designed for profiles and plates | 1,05 | 0,6 | | | |
| 24 T 10 | PP homopolymer 40% talcum filled, basic stabilization. Extrusion profiles for self-coloring | | 2,5 | | | |
| 24 T 20 | PP copolymer 40% fine white and aesthetic talcum. Easy self-coloring, extrusion profiles | 1,24 | 1,5 | | | |
| 51 T 10 | PP homopolymer 10% filled fine white talcum, aesthetic grade, basic stabilization, medium flow, easy to color, injection moulding | 0,97 | 23 | | | |
| 31 G 23 | PP copolymer, impact modified, 15% glassfibre, aesthetic, easy to color, stress withering improved in natural. Suitable on other colors, injection molding | 1,01 | 7 | | | |
| 32 G 12 | PP homopolymer 20% glassfibre, natural or black. Designed for water contact applications, injection moulding | 1,03 | 3,5 | | | |
| 33 G 12 | PP homopolymer 30% glassfibre, natural or black. Designed for water contact applications, injection moulding | 1,12 | 3 | | | |

| Ash Content | Flexural modulus | Tensile modulus | Tensile stress at yield | | ct Strengh notched | VICAT B50 (50N) | HDT/A (1,82 MPa) |
|--------------|------------------|-----------------|-------------------------|------------------|-----------------------|--------------------|---------------------|
| 625° C [%] | [MPa] | [MPa] | [MPa] | 23°C [kJ/m²] | 23°C [kJ / m²] | °C | °C |
| ISO 3451 | ISO 178 | ISO 527 | ISO 527 | ISO 179 / 1eA | ISO 180 / 1A | ISO 306 | ISO 75A |
| | | | | | | | |
| 30 | 5000 | 4700 | 55 | 25 | 24 | - | 135 |
| 22 | 2500 | 2100 | 27 | 55 | 50 | 70 | - |
| 40 | 3200 | 3300 | 32 | 3 | 4 | | 58 |
| 40 | 2900 | 3500 | 25 | 5 | 6 | - | 65 |
| 10 | 2000 | 2300 | 35 | 2,5 | 3 | | 55 |
| 16 | 2800 | 3000 | 55 | 11 | 13 | - | 125 |
| 20 | 3900 | 5100 | 70 | 10 | 10 | - | 140 |
| 30 | 5500 | 7000 | 80 | 11 | 12 | - | 140 |

High quality Prime Compounds

SCOLEFIN® PP compounds form just part of an extensive portfolio of high quality plastics compounds from Ravago. Ravago has been manufacturing compounds for over 50 years and it is this experience that allows converters and end users to have the confidence to specify our products. The prime portfolio consists of the following brands:

| SCOLEFIN® | PP | SICOKLAR® | PC |
|-----------|-----------|--------------|-----|
| RAVAMID® | PA6, PA66 | SICOSTIROLO® | PS |
| MABLEX® | PC / ABS | POLYFAST® | ASA |
| SICOFLEX® | ABS | VERPLEN® | ASA |

SCOLEFIN® PP compounds

SCOLEFIN® PP compounds offer the end user a broad range of solutions via a wide product portfolio that includes:

| Unfilled black, colored and natural grades | Elastomer modified |
|--|----------------------------------|
| Talc or CaCO3 filled (5-70%) black/natural | UV and heat stabilized |
| Glass fibre reinforced (5-50%) black | MFI range from 1.5 to 40 g/10min |
| Combined filling | Tailor made compounds |

The extended knowledge of Ravago in compounding makes the SCOLEFIN® PP the best solution for a wide variety of applications. The combination of additives gives to the SCOLEFIN® great characteristics that can be applied to:

| AUTOMOTIVE | Cowl vent grill / water deflector Wheel arch liner Filter housing Under body parts Battery trays | Headlight housing Bumper mount Inlet manifold Toolbox | NON AUTOMOTIVE | Garden furniture Artificial wood profiles White goods parts Parts of appliances |
|------------|--|--|-------------------|--|



The Ravago Group is a leading international supplier of plastics and rubber to customers and end-users in almost every corner of the world. In 1961, long before plastics recycling became fashionable, Ravago pioneered the reprocessing of industrial plastic waste and its conversion into a new raw material source.

Ravago Group is active in the compounding, distribution, recycling and resale of plastics and rubber. Today, with more than 55 years of market presence, Ravago ranks as one of Europe's oldest and most prominent plastic enterprises.

Whilst high quality recycled polymers have been finding their way into non visual automotive applications for some time, visual parts have been always produced from prime polymers.



www.ravagomanufacturing.com

