

# Mablex<sup>®</sup> PCX

PC/ABS Blend  
Industrial Quality Compound

## Description:

PC/ABS blend general purpose grade

## General

Density	ISO 1183	1.13	g/cm <sup>3</sup>
Linear mould shrinkage	ISO 2577	0.5-0.7	%
MFI (260°C/5kg)	ISO 1133	30	g/10min

## Thermal

HDT/A (1,82MPa)	ISO 75A	108	°C
Vicat softening point (B50 (50N))	ISO 306	120	°C
Vicat softening point (A50(10N))	ISO 306	126	°C
Ball pressure test (75°C)	IEC 335	Pass	°C

## Mechanical

Izod notched impact strength (23°C)	ISO 180/A	25	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	45	MPa
Tensile stress at break	ISO 527	35	MPa
Elongation at break	ISO 527	28	%
Flex modulus	ISO 178	2300	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
May 2017