

Ravamid® B N GR 133 GREY

Polyamide 6 Industrial Quality Compound

Description:

Polyamide 6 grey containing recycled material, impact modified

General

| Density | ISO 1183 | 1.11 | g/cm³ |
|--------------------------------|----------|------|-------|
| Mold shrinkage (Parallel) | | 1.04 | % |
| Mold shrinkage (Perpendicular) | | 1.12 | % |

Thermal

| HDT/A (1,82MPa) | ISO 75A | 60 | °C |
|-----------------------------------|---------|-----|----|
| Vicat softening point (B50 (50N)) | ISO 306 | 200 | °C |

Mechanical

| | | Ī | | |
|--|-------------|------|-------|---|
| Izod notched impact strength (23°C) | ISO 180/A | 10.5 | kJ/m² | |
| Izod notched impact strength (-30°C) | ISO 180/A | 8 | kJ/m² | |
| Charpy notched impact strength (23 °C) | ISO 179/1eA | 8 | kJ/m² | |
| Charpy notched impact strength (-30°C) | ISO 179 | 10.5 | kJ/m² | |
| Tensile stress at yield | ISO 527 | 50 | MPa | |
| Tensile stress at break | ISO 527 | 40 | MPa | |
| Elongation at break | ISO 527 | 65 | % | |
| Flex modulus | ISO 178 | 1900 | MPa | ŀ |
| L Company of the Comp | | | | |

Flammability

| Flammability (3,2mm) | UL94 | НВ | |
|---------------------------------------|----------------|-----|----|
| Flammability (1,6mm) | UL94 | НВ | |
| Glow wire flammability index (2,0 mm) | IEC 60695-2-12 | 650 | °C |

Various

| Humidity | ISO 960 | ≤0.25 | % | |
|----------|---------|-------|---|--|

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A Tel: +32 (0)14 67 25 11 B - 2370 Arendonk Fax: +32 (0)14 67 20 12