



Preliminary Technical Data Sheet

RAVAMID[®] C GF 15 T BK45

Polyamide Copolymer Blend 6/66 Black containing recycled material, 15% glass fiber reinforced, also available Heat Stabilized (H) and UV Stabilized (UV)

PROPERTIES	NORM		UNIT	VALUE
	ISO	ASTM		
<u>GENERAL</u>				
Density	1183	D792	g/cm3	1.18
Linear mould shrinkage (Parallel)	/	D955	%	0.30
Linear mould shrinkage (Perpendicular)	/	D955	%	0.90
Melt Flow Index 250°C/2.16Kg	1133	D1238	g/10 min	-
Humidity	960	-	%	≤0.20
<u>TERMICHE/ THERMAL</u>				
VICAT B50	306	D1525	°C	195
HDT/A (annealed)	75	D648	°C	180
<u>MECCANICHE/ MECHANICAL</u>				
Tensile strength (yield)	527	D638	MPa	-
Tensile strength (break)	527	D638	MPa	90
Elongation at break	527	D638	%	5
Flexural modulus	178	D790	MPa	4200
Tensile modulus	527	D638	MPa	3800
Izod Impact + 23°C (notched)	180/1A	D256	KJ/m2	14
Charpy Impact + 23°C (notched)	179/1U	-	KJ/m2	65
Charpy Impact + 23°C (notched)	179/1A	-	KJ/m2	13
<u>FLAMMABILITY</u>				
Burning rate (FMVSS 302)	ISO 3795	-	mm/min	<100
Flammability 3,2 mm	UL94	-	-	HB
Flammability 1.6 mm	UL94	-	-	HB
Flammability 0.75 mm	UL94	-	-	-
Glow Wire Flammability Index 2,0 mm	IEC 60695-2-12		°C	650
Glow Wire Ignitability Temperature 1,2 mm	IEC 60695-2-13		°C	-
<u>ELECTRICAL</u>				
Dielectric rigidity (Oil 1mm)	IEC 60243-1		KV/mm	-
Surface resistivity	IEC 60093		Ohm	-
Volume resistivity	IEC 60093		Ohmxcm	-
CTI Comparative Tracking Index	IEC 60112		V	-

®Trademark property of Ravago Italia Spa

issued on March 2011

The information and data contained herein do not constitute sales specifications. The product properties may be changed without notice. No liability, warranty or guarantee of product performance is created by this document. It is the Buyer's responsibility to determine whether Ravago products are appropriate for Buyer's use and to ensure that Buyer's workplace and disposal practices are in compliance with applicable laws and regulations. No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.