

Ravamid® R200 GF 10

Polyamide 6
Prime Compound

Description:

Polyamide 6 10% Glass Fiber filled, prime quality compound, available in custom colors also heat stabilized (H) and UV stabilized (UV)

General

Density	ISO 1183	1.18	g/cm ³
Water absorption (23°C;50%RH)	ASTM D570	1.1	%
Mold shrinkage (Parallel)		0.7	%
Mold shrinkage (Perpendicular)		1.2	%

Thermal

HDT/A (1,82MPa)	ISO 75A	100	°C
Vicat softening point (B50 (50N))	ISO 306	200	°C
Melting point	ISO 3146	230	°C
Ball pressure test (125°C)	IEC 335	Pass	°C

Mechanical

Izod notched impact strength (23°C)	ISO 180/A	5	kJ/m ²
Izod unnotched impact strength (23 °C)	ISO 180	25	kJ/m ²
Tensile stress at break	ISO 527	60	MPa
Elongation at break	ISO 527	5	%
Flex modulus	ISO 178	3000	MPa
Flexural strength (+23°C)	ISO 178	80	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Nov 2011