

Ravaplen® 62 T 40

Polypropylene
Near Prime Compound

Description:

PP 16% mineral filled intended for injection moulding. Ravaplen 62 T 40-9 has been developed especially for automotive industry and is based on industrial quality raw material.

General

MFI (230°/2,16kg)	ISO 1133	13	g/10min
Density	ISO 1183	1,06	g/cm ³

Thermal

HDT/A (1,82MPa)	ISO 75A	60	°C
-----------------	---------	----	----

Mechanical

Izod notched impact strength (23°C)	ISO 180	6	kJ/m ²
Izod unnotched impact strength (23 °C)	ISO 180	NB	kJ/m ²
Tensile stress at yield	ISO 527	24	MPa
Tensile modulus	ISO 527	1800	MPa
Flex modulus	ISO 178	1900	MPa

Various

Ash content (600 °C)	ISO 3451	16	%
----------------------	----------	----	---

Remark:

Coloured upon request

Ravaplen E25042
Ravaplen E25018
Ravaplen E20000

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Dec 2018