

# Ravaplen® 62 T 41

Polypropylene  
Near Prime Compound

## Description:

PP Copolymer, near to prime compound, 20% talc reinforced, different colours on request

## General

MFI (230°/2,16kg)	ISO 1133	15	g/10min
Density	ISO 1183	1,05	g/cm <sup>3</sup>

## Thermal

Vicat softening point (B50 (50N))	ISO 306	57	°C
-----------------------------------	---------	----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	8	kJ/m <sup>2</sup>
Izod notched impact strength (-30°C)	ISO 180	3	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	10	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	20	MPa
Elongation at yield	ISO 527	8	%
Elongation at break	ISO 527	100	%
Tensile modulus	ISO 527	1500	MPa
Flex modulus	ISO 178	1600	MPa

## Various

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Jul 2018