

Ravaplen® 72 T 41

Polypropylene
Near Prime Compound

Description:

PP Copolymer, near to prime compound, 20% talc reinforced, excellent scratch resistance, UV stabilised, for automotive interior trims, different colours on requests

General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	1,02	g/cm ³

Thermal

Vicat softening point (B50 (50N))	ISO 306	58	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23°C)	ISO 180	8	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179	6	kJ/m ²
Tensile stress at yield	ISO 527	23	MPa
Elongation at yield	ISO 527	8	%
Tensile modulus	ISO 527	1500	MPa
Flex modulus	ISO 178	2000	MPa

Various

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---

Remark:

Preliminary version

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Apr 2019