

# Ravaplen® 72 T 43

Polypropylene  
Near Prime Compound

## Description:

PP Copolymer, ECO compound, 20% talc reinforced, excellent scratch resistance, UV stabilised, for automotive interior trims, different colours on request

## General

MFI (230°/2,16kg)	ISO 1133	15	g/10min
Density	ISO 1183	1,03	g/cm <sup>3</sup>

## Thermal

HDT/A (1,82MPa)	ISO 75A	60	°C
Vicat softening point (B50 (50N))	ISO 306	60	°C

## Mechanical

Izod notched impact strength (23°C)	ISO 180	13	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	11	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	20	MPa
Elongation at yield	ISO 527	5	%
Tensile modulus	ISO 527	1700	MPa
Flex modulus	ISO 178	1900	MPa

## Various

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Apr 2019