

# Scolefin<sup>®</sup> 53 T 10

Polypropylene  
Prime Compound

## Description:

PPH, 30% talc filled, natural

## General

MFI (230°/2,16kg)	ISO 1133	12	g/10min
Density	ISO 1183	1.15	g/cm <sup>3</sup>

## Thermal

Vicat softening point (B50 (50N))	ISO 306	100	°C
-----------------------------------	---------	-----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	3	kJ/m <sup>2</sup>
Flex modulus	ISO 178	3000	MPa

## Remark:

Different colors available:

- Scolefin 53 T 10-9: black version
- Scolefin 53 T 10-0: natural version

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Apr 2018