



Polycarbonate Industrial Quality Compound

Description:

PC, high flow

General

MFI (300°C/1,2kg)	ISO 1133	25	g/10min
Density	ISO 1183	1.20	g/cm³
Linear mould shrinkage	ISO 2577	0.5-0.7	%

Thermal

HDT/A (1,82MPa)	ISO 75A	130	°C
Vicat softening point (B50 (50N))	ISO 306	140	°C
Vicat softening point (A50(10N))	ISO 306	145	°C
Ball pressure test (125°C)	IEC 335	Pass	°C

Mechanical

	 -		
Izod notched impact strength (23°C)	ISO 180/A	40	kJ/m²
Izod notched impact strength (-30°C)	ISO 180/A	10	kJ/m²
Tensile stress at yield	ISO 527	50	MPa
Tensile stress at break	ISO 527	40	MPa
Elongation at break	ISO 527	30	%
Flex modulus	ISO 178	2400	MPa

Flammability

Glow wire flammability index (2,0 mm)	IEC 60695-2-12	850	°C
Flammability (1,0 mm)	UL94	V2	

Remark:

UL94 officially approval file number: E103497

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.