

## Sicostirolo® CR H 3441

# High Impact Polystyrene Industrial Quality Compound

### Description:

High impact polystyrene, natural

#### General

General			
MFI (200°C/5kg)	ISO 1133	5	g/10min
Density	ISO 1183	1.05	g/cm³
Linear mould shrinkage	ASTM D955	0.4-0.7	%
Thermal			
HDT/A (1,82MPa)	ISO 75A	70	°C
Vicat softening point (B50 (50N))	ISO 306	82	°C
Vicat softening point (A50(10N))	ISO 306	90	°C
Mechanical			
Izod notched impact strength (23°C)	ISO 180	7	kJ/m²
Tensile stress at yield	ISO 527	20	MPa
Tensile stress at break	ISO 527	16	MPa
Elongation at break	ISO 527	10	%
Flex modulus	ISO 178	2200	МРа
Flammability			
Flammability (3,2mm)	UL94	НВ	
Flammability (1,6mm)	UL94	НВ	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	550	°C
Various			
Surface resistivity	IEC 60093	1E15	Ohm

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

IEC 60093

IEC 60112

IEC 60243-1

### **Ravago Group Headquarters**

Volume resistivity

CTI

Dielectric rigidity (Oil 1mm)

1E15

60

500

Ohm.cm

kV/mm