

Verplen® C 30 58 ACL

Polypropylene
Prime Compound

Description:

Polypropylene copolymer 30% glass fiber filled chemically grafted

General

MFI (230°/2,16kg)	ISO 1133	13	g/10min
Density	ISO 1183	1,13	g/cm ³
Linear mould shrinkage	ASTM D955	0,2-0,4	%

Thermal

HDT/A (1,82MPa)	ISO 75A	120	°C
Vicat softening point (B50 (50N))	ISO 306	110	°C
Ball pressure test (75°C)	IEC 335	Pass	°C

Mechanical

Izod notched impact strength (23°C)	ASTM D256	13	J/m
Izod unnotched impact strength (-30 °C)	ISO 180	5	kJ/m ²
Tensile stress at break	ISO 527	75	MPa
Elongation at break	ISO 527	4	%
Tensile modulus	ISO 527	5800	MPa
Flex modulus	ISO 178	5200	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	35	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Surface resistivity	IEC 60093	10E13	Ohm
Volume resistivity	IEC 60093	10E13	Ohm.cm
Dielectric rigidity (Oil 1mm)	IEC 60243-1	20	kV/mm
CTI	IEC 60112	600	V

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Dec 2017