

AKROMID®

B3 GF 10 natural (2829)

PA6 GF10

AKROMID® B3 GF 10 natural (2829) is a 10% glass fibre reinforced polyamide 6 with medium stiffness and strength and light inherent color.

Properties

Modulus	Strength	Impact
4.800 MPa	105 MPa	47 kJ/m ²

Mechanical Properties

Tensile modulus ISO 527-2	1 mm/min d.a.m.	4800 MPa
	1 mm/min conditioned	2700 MPa
Tensile stress at break ISO 527-2	5 mm/min d.a.m.	105 MPa
	5 mm/min conditioned	55 MPa
Tensile strain at break ISO 527-2	5 mm/min d.a.m.	3 %
	5 mm/min conditioned	17 %
Flexural modulus ISO 178	2 mm/min d.a.m.	3500 MPa
Flexural strength ISO 178	2 mm/min d.a.m.	150 MPa
Charpy impact strength ISO 179-1/1eU	23°C d.a.m.	47 kJ/m ²
	23°C conditioned	115 kJ/m ²
	-30°C d.a.m.	41 kJ/m ²
Charpy notched impact strength ISO 179-1/1eA	23°C d.a.m.	5 kJ/m ²
	23°C conditioned	8 kJ/m ²
	-30°C d.a.m.	5 kJ/m ²

Thermal Properties

Temperature of deflection under load HDT/A ISO 75	1,8 MPa	200 °C
Temperature of deflection under load HDT/B ISO 75	0,45 MPa	220 °C
Melting temperature ISO 11357-3	DSC, 10K/min	220 °C
Temperature index for 50% loss of tensile strength IEC 60216	5.000 h 20.000 h	160 - 175 °C 130 - 150 °C

Flammability

Flammability UL 94	1,6 mm Wall thickness	HB Class
GWFI IEC 60695-2-12	1,6 mm Wall thickness	650 °C
Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+

General Properties

Density ISO 1183	23°C	1,2 g/cm ³
Humidity absorption ISO 1110	70°C, 62% r.H.	2,6 - 3,4 %
Water absorption ISO 62	23°C, saturated	8,5 - 9,0 %
Molding shrinkage ISO 294-4	flow transverse	0,4 % 0,7 %

Electrical Properties


Volume resistivity IEC 62631-3-1	d.a.m. conditioned	10 ¹³ Ω x cm 10 ¹⁰ Ω x cm
--	-----------------------	--

Surface resistivity	d.a.m.	10¹² Ω
IEC 62631-3-2	conditioned	10¹⁰ Ω

Comparative tracking index	Test liquid A	600 V
IEC 60112		

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	240 - 290 °C
3	Nozzle temperature	260 - 300 °C
4	Melt temperature	270 - 290 °C
5	Mold temperature	80 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min