

AKROMID® B3 LA black (4056)

PA6

AKROMID® B3 LA black (4056) is an unreinforced polyamide 6. It is characterised by very good laser markable properties and is therefore suitable for handles, housings and covering parts for the industry and the automotive sector.

Features

laser markable

Properties

Modulus	Strength	Impact
3.400 MPa	85 MPa	180 kJ/m ²

Mechanical Properties

Tensile modulus ISO 527-2	1 mm/min d.a.m.	3400 MPa
	1 mm/min conditioned	1000 MPa
Tensile stress at yield ISO 527-2	50 mm/min d.a.m.	85 MPa
	50 mm/min conditioned	45 MPa
Tensile strain at break ISO 527-2	50 mm/min d.a.m.	20 %
	50 mm/min conditioned	> 50 %
Flexural modulus ISO 178	2 mm/min d.a.m.	3000 MPa
Flexural strength ISO 178	2 mm/min d.a.m.	115 MPa
Flexural strain at break ISO 178	2 mm/min d.a.m.	6,5 %
Charpy impact strength ISO 179-1/1eU	23°C d.a.m.	no break
	23°C conditioned	no break
Charpy notched impact strength ISO 179-1/1eA	23°C d.a.m.	3 kJ/m²
	23°C conditioned	20 kJ/m²
	-30°C d.a.m.	5 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A ISO 75	1,8 MPa	60 °C
Temperature of deflection under load HDT/B ISO 75	0,45 MPa	160 °C
Melting temperature ISO 11357-3	DSC, 10K/min	220 °C

Flammability

Flammability UL 94	1,6 mm Wall thickness	V-2 Class
GWFI IEC 60695-2-12	1,6 mm Wall thickness	750 °C
GWIT IEC 60695-2-13	1,6 mm Wall thickness	675 °C
Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+

General Properties

Density ISO 1183	23°C	1,13 g/cm³
Humidity absorption ISO 1110	70°C, 62% r.H.	2,5 %
Molding shrinkage ISO 294-4	flow	1,0 - 1,2 %
	transverse	1,1 - 1,3 %

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	220 - 270 °C
3	Nozzle temperature	230 - 300 °C
4	Melt temperature	240 - 270 °C
5	Mold temperature	40 - 80 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min