

AKROTEK® PRELIMINARY

PK-VM GF 30 FR natural (8448)

PK GF30 FR(40)

AKROTEK® PK-VM GF 30 FR natural (8448) is a 30% glass fibre reinforced, flame retardant and process improved Polyketone compound. The flame retardant system is free of red phosphorous and halogens. Due to its good chemical resistance, good dimensional stability and high elongation at break it is suitable for high voltage components in e-mobility.

Features

hydrolysis / chemically stabilised flame retardant
process improved E&E E-Mobility

Regulatory



Properties

Modulus	Strength	Impact
8.600 MPa	125 MPa	70 kJ/m ²

Mechanical Properties

Tensile modulus ISO 527-2	1 mm/min d.a.m.	8600 MPa
Tensile stress at break ISO 527-2	5 mm/min d.a.m.	125 MPa
Tensile strain at break ISO 527-2	5 mm/min d.a.m.	3,5 %
Charpy impact strength ISO 179-1/1eU	23°C d.a.m. -30°C d.a.m.	70 kJ/m ² 80 kJ/m ²
Charpy notched impact strength ISO 179-1/1eA	23°C d.a.m. -30°C d.a.m.	13 kJ/m ² 13 kJ/m ²

Thermal Properties

RTI electrical UL 746B	UL 0,8mm Wall thickness	105 °C
	UL 1,6mm Wall thickness	105 °C
	UL 3,2mm Wall thickness	105 °C
RTI impact UL 746B	UL 0,8mm Wall thickness	70 °C
	UL 1,6mm Wall thickness	70 °C
	UL 3,2mm Wall thickness	80 °C
RTI strength UL 746B	UL 0,8mm Wall thickness	115 °C
	UL 1,6mm Wall thickness	115 °C
	UL 3,2mm Wall thickness	125 °C
Temperature of deflection under load HDT/A ISO 75	1,8 MPa	213 °C
Melting temperature ISO 11357-3	DSC, 10K/min	220 °C
Ball pressure test IEC 60695-10-2		> 115 °C
Coefficient of linear thermal expansion ISO 11359-1/2	23°C to 80°C parallel	0,14 10 ⁻⁴ /K
	23°C to 80°C transverse	1,19 10 ⁻⁴ /K

Flammability

Flammability UL 94	UL 0,8 mm Wall thickness	V-0 Class
	UL 1,6 mm Wall thickness	V-0 Class
	UL 3,2 mm Wall thickness	V-0 Class
GWFI IEC 60695-2-12	UL 0,8 mm Wall thickness	960 °C
	UL 1,6 mm Wall thickness	960 °C
	UL 3,2 mm Wall thickness	960 °C
GWIT IEC 60695-2-13	UL 0,8 mm Wall thickness	825 °C
	UL 1,6 mm Wall thickness	825 °C
	UL 3,2 mm Wall thickness	850 °C
HWI UL 746A	UL 0,8 mm Wall thickness	0 PLC
	UL 1,6 mm Wall thickness	0 PLC
	UL 3,2 mm Wall thickness	0 PLC
HAI UL 746A	UL 0,8 mm Wall thickness	0 PLC
	UL 1,6 mm Wall thickness	0 PLC
	UL 3,2 mm Wall thickness	0 PLC

Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+
---	------------------	---

General Properties


Density ISO 1183	23°C	1,48 g/cm ³
Humidity absorption ISO 1110	70°C, 62% r.H.	0,4 - 0,6 %
Molding shrinkage ISO 294-4	flow transverse	0,3 - 0,5 % 0,8 - 1,0 %

Electrical Properties

Volume resistivity IEC 62631-3-1	 d.a.m.	10 ¹⁰ Ω x cm
Surface resistivity IEC 62631-3-2	 d.a.m.	10 ¹³ Ω
Comparative tracking index IEC 60112	 Test liquid A	600 V
Comparative tracking index ASTM D3638		0 PLC
Dielectric strength IEC 60243	1 mm	29 kV/mm
Inclined-Plane Tracking, IPT ASTM D2303-13		1 kV

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	210 - 240 °C
3	Nozzle temperature	230 - 240 °C
4	Melt temperature	230 - 240 °C
5	Mold temperature	60 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 50 bar
	Injection speed	medium
	Screw speed	5 - 10 m/min