



creative thermoplastic compounds

PB300G6/PB303G6

Release Date: 02/11/2012

30% Glass Fiber Reinforced, Heat Stabilized Polyamide 6 for Injection Moulding applications.
ISO

PHYSICAL PROPERTIES	UNIT	TEST METHOD	VALUES
DENSITY	g/cm ³	ISO-1183	1.36
WATER ABSORPTION (SATURATION)	%	ISO-62	6.6
MOISTURE ABSORPTION 23° C, 50% RH (SATURATION)	%	ISO-62	2.1
MOULD SHRINKAGE	%	ISO-2577	0.3-0.7
MECHANICAL PROPERTIES	UNIT	TEST METHOD	VALUES
TENSILE YIELD STRENGTH	MPa	ISO-527	180
TENSILE MODULUS	MPa	ISO-527	9000
STRAIN @ BREAK	%	ISO-527	3.5
FLEXURAL STRENGTH	MPa	ISO-178	250
FLEXURAL MODULUS	MPa	ISO-178	8500
NOTCHED IZOD IMPACT STRENGTH +23°C	Kj/m ²	ISO-180	12
NOTCHED IZOD IMPACT STRENGTH -30°C	Kj/m ²	ISO-180	9
NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	16
NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	10
UN NOTCHED CHARPY IMPACT STRENGTH +23°C	Kj/m ²	ISO-179	75
UN NOTCHED CHARPY IMPACT STRENGTH -30°C	Kj/m ²	ISO-179	70
THERMAL PROPERTIES	UNIT	TEST METHOD	VALUES
HDT AT LOAD 1.8 Mpa	°C	ISO-75	205
HDT AT LOAD 0.45 Mpa	°C	ISO-75	217
FLAMMABILITY	mm/min	FMVSS302	14
UL FLAMMABILITY		UL-94 3mm	H.B.
MELTING POINT	°C	ISO-11357	218
ELECTRICAL PROPERTIES	UNIT	TEST METHOD	VALUES
SURFACE RESISTANCE	Ohm	IEC 60093	10 ¹²
VOLUME RESISTANCE	Ohm x m	IEC 60093	10 ¹⁵
DIELECTRIC STRENGTH	kV/mm	IEC 60250	80
DIELECTRIC CONSTANT AT 1MHZ	kV/mm	IEC 60250	3.8

The information contained in this website is supplied in good faith. However, it is given purely as an indication. It shall not be construed in any way as formal commitment or warranty on our part. Notably in respect of the eventual infringement of any rights of third parties who may use our products. We remain at your entire disposal for any further information that you may require.