

## TECHNICAL DATA SHEET

# RILSAMID® AESNO P302 TL

## POLYAMIDE 12 PELLET

RILSAMID® AESNO P302 TL is a polyamide 12 compound. This natural plasticized & impact-modified grade is designed for tube extrusion, including air brake tubing (HIPHL).

**Designation :** ISO 16396 - PA12-IP, EG1HL, C22-004

### TYPE

PA12-IP

### MAIN APPLICATIONS

- Heavy Truck - Air Brake Lines

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

## RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	13	cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Charpy unnotched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	No Break / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	> 50 / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	24 / 24	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	28 / 24	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	475 / 430	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 46	kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	4 / 6	kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 378	MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	174	°C	ISO 11357-1/-3

# RILSAMID® AESNO P302 TL

## ELECTRICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Surface resistivity, 23°C (73°F)	- / 7.0E+13	Ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73°F)	- / 1.0E+12	Ohm.m	IEC 62631-3-1
Comparative tracking index, 23°C (73°F)	- / 600		IEC 60112
Dielectric stress, 23°C (73°F)	- / 41	kV/mm	IEC 60243-1

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Water absorption, 23°C (73°F), immersion, equilibrium	1.2	%	ISO 62
Specific gravity, 23°C (73°F)	1.03	g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

Available packaging:

- 25 kg / 55 lb bags
- 550 kg rigid containers


## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## DIAGRAMS



# RILSAMID® AESNO P302 TL

