

## TECHNICAL DATA SHEET

# RILSAMID® MA 4411 NAT

## POLYAMIDE 12 PELLET

RILSAMID® MA 4411 NAT a polyamide 12 compound. This natural plasticized and impact-modified grade is designed for tube extrusion. It is a market standard to produce automotive fuel lines.

### TYPE

PA12-IP

### MAIN APPLICATIONS

- Light Vehicle

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

### ADDITIVES

- Heat Stabilized
- Light Stabilized

## RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	14	cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 63		ISO 868
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 23	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 25	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	470 / 470	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	No Break / No Break		ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 6	kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 420	MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3

# RILSAMID® MA 4411 NAT

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.03	g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

Available packaging:

- 25 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

## REGIONAL AVAILABILITY

Europe