

## TECHNICAL DATA SHEET

# RILSAMID® AECV BLACK P40 T8L

## POLYAMIDE 12 PELLET

RILSAMID® AECV BLACK P40 T8L resin is a black colored polyamide 12 compound. This plasticized grade is designed for cable coating.

**Designation :** ISO 16396 - PA12-P, KG1HL, C14-004

### TYPE

PA12-P

### MAIN APPLICATIONS

- LT Performance Wire - Growth
- Cables Antitermites
- Cable

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General

### ADDITIVES

- Heat Stabilized
- Light Stabilized

## RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 2.16 kg (455°F / 4.4 lb)	23	cm <sup>3</sup> /10min	ISO 1133

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Charpy unnotched impact strength, 23°C (73°F)	- / No Break		ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break		ISO 179 1eU
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 27	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 26	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 420	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 7	kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 5	kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 420	MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	172	°C	ISO 11357-1/-3

# RILSAMID® AECV BLACK P40 T8L

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.01	g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

Available packaging:

- 25 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 250°C / 270°C (445°F / 480°F / 520°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours