

## TECHNICAL DATA SHEET

# PEBAX<sup>®</sup> CLEAR 1200

## POLYETHER BLOCK AMIDE PELLET

Pebax<sup>®</sup> Clear 1200 combines high transparency and high rigidity with the unique performance of Pebax<sup>®</sup> thermoplastic elastomer. It is produced from a renewable and sustainable source (castor oil).

### TYPE

PEBA

### MAIN APPLICATIONS

- Footwear - Outsole/Components

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Extrusion - General
- Film Extrusion
- Injection Molding
- Tube Extrusion

## RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Shrinkage, Parallel (t+24h)	0.5	%	ISO 294-4
Shrinkage, Normal (t+24h)	0.5	%	ISO 294-4

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Shore D, 15 s	- / 73		ISO 868
Nominal strain at break, 23°C (73°F), 50 mm/min	- / > 50	%	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 5.1	%	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 43	MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 1300	MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 8	kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 12	kJ/m <sup>2</sup>	ISO 179 1eA
Flexural modulus, 23°C (73°F)	- / 1200	MPa	ISO 178

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	180	°C	ISO 11357-1/-3

## OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Bio-based carbon content, Measured	94	%	ASTM D6866
Specific gravity, 23°C (73°F)	1.03	g/cm <sup>3</sup>	ISO 1183-1

# PEBAX® CLEAR 1200

---

## PACKAGING

Available packaging:

- 25 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 230°C / 260°C / 290°C (445°F / 500°F / 555°F)
- Typical mold temperature - Injection molding: 20-80°C (70-175°F)
- Drying time and temperature: 70-80°C (160-175°F) / 4-6 hours

## SPECIAL CHARACTERISTICS

- Transparent

## REGIONAL AVAILABILITY

Asia Pacific, Europe, Latin America and the Caribbean, Middle East, Northern America