



AFFINITY™ GA 1950

The Dow Chemical Company - Polyolefin Plastomer

Monday, November 4, 2019

General Information

Product Description

- Ultra high clarity, low density, low viscosity polyolefin
- Excellent thermal stability
- Low Tg (Excellent low temperature properties)
- Excellent flexibility
- Non corrosive
- Excellent color and odor
- Excellent compatibility with a wide range of polymers
- Low crystallinity (can be heavily filled)
- Low density (better mileage)
- Excellent adhesion to diverse substrates when formulated

Complies with:

- U.S. FDA FCN 424

Consult the regulations for complete details.

AFFINITY* GA 1950 Polyolefin Plastomer (POP) is produced via INSITE* Technology from Dow Plastics. This product can be used in applications such as polymer modification (i.e. flow enhancement and property enhancement), masterbatch/additive carrier, and hot melt adhesives.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• FDA FCN 424		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.876		ASTM D792
Gardner Color	2.00		ASTM D6290
Volatile Matter ²	< 0.15	%	ASTM D3030
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	255	psi	ASTM D638
Tensile Elongation (Break)	190	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-69.0	°F	Internal Method
Melting Temperature (DSC)	158	°F	Internal Method
Fill Analysis	Nominal Value	Unit	Test Method
Brookfield Viscosity (350°F)	17.0	Pa·s	ASTM D1084

Notes

¹ Typical properties: these are not to be construed as specifications.

² Modified for polyolefins. Change the temperature used to 100°C +/-3 and the amount of sample to 20 grams.