



Adsyl 5 C 30 F ST

LyondellBasell Industries - Polyolefin

Tuesday, November 5, 2019

General Information

Product Description

Adsyl 5 C 30 F ST is an advanced polyolefin, specially designed for use as a sealing or metallized layer in co-extruded film applications. This grade features a very low seal initiation temperature and excellent optics. It does not contain slip or anti-block additives.

For regulatory information please refer to Adsyl 5 C 30 F ST Product Stewardship Bulletin (PSB).

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Optical Properties • Heat Sealable	• Low Temperature Heat Sealability • Metallizable	
Uses	• Bi-axially Oriented Film • Cast Film • Film	• Food Packaging • Laminates • Packaging	• Shrink Wrap
Processing Method	• Bi-axially Oriented Film • Cast Film	• Coextruded Film • Double-Bubble Film	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-3/25
MD : 2.0 mil, Cast Film	37700	psi	
TD : 2.0 mil, Cast Film	34800	psi	
Tensile Stress			ISO 527-3/500
MD : Yield, 2.0 mil, Cast Film	2180	psi	
TD : Yield, 2.0 mil, Cast Film	2030	psi	
Tensile Stress			ISO 527-3/500
MD : Break, 2.0 mil, Cast Film	5950	psi	
TD : Break, 2.0 mil, Cast Film	5950	psi	
Tensile Elongation			ISO 527-3/500
MD : Break, 2.0 mil, Cast Film	900	%	
TD : Break, 2.0 mil, Cast Film	900	%	
Tensile Elongation			ISO 527-3/500
MD : Yield, 2.0 mil, Cast Film	18	%	
TD : Yield, 2.0 mil, Cast Film	16	%	
Seal Initiation Temperature	221	°F	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	142	°F	ISO 75-2/B
Vicat Softening Temperature	225	°F	ISO 306/A50
Melting Temperature	270	°F	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 1.97 mil)	91		ASTM D2457

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Adsyl 5 C 30 F ST

LyondellBasell Industries - Polyolefin

Optical	Nominal Value	Unit	Test Method
Haze (1.97 mil)	0.200	%	ASTM D1003

Notes

¹ Typical properties: these are not to be construed as specifications.