



Celcon® LU02

Celanese Corporation - Acetal (POM) Copolymer

Saturday, November 2, 2019

General Information

Product Description

Celcon® acetal copolymer grade LU02 is UV stabilized material displaying a reduced gloss over standard UV acetal grades.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Low Gloss	• UV Stabilized	
RoHS Compliance	• Contact Manufacturer		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	20	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.6	%	
Flow	1.9	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	367000	psi	ISO 527-2/1A
Tensile Stress (Yield)	8120	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	11	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	363000	psi	ISO 178
Flexural Stress (3.5% Strain)	9720	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	1.8	ft-lb/in ²	
73°F	1.8	ft-lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	194	°F	ISO 75-2/A
Vicat Softening Temperature	322	°F	ISO 306/B50
Melting Temperature ²	333	°F	ISO 11357-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 347	°F
Middle Temperature	338 to 356	°F
Front Temperature	347 to 365	°F
Nozzle Temperature	365 to 383	°F
Processing (Melt) Temp	356 to 383	°F
Mold Temperature	176 to 221	°F

Celcon® LU02

Celanese Corporation - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Injection Rate	Slow	
Back Pressure	< 580	psi

Injection Notes

Zone4 temperature: 180 to 190°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min