



Celcon® M270UV

Celanese Corporation - Acetal (POM) Copolymer

Saturday, November 2, 2019

General Information

Product Description

Celcon® M270UV is an acetal copolymer developed as a natural UV light stabilized lower molecular weight, high-flow grade designed for superior moldability in multi-cavity or hard to fill injection mold.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Good Moldability • High Flow	• Low Molecular Weight • UV Stabilized	
RoHS Compliance	• Contact Manufacturer		
Appearance	• Natural Color		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	23	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.6	%	
Flow	1.7	%	
Water Absorption (Saturation, 73°F)	0.75	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	406000	psi	ISO 527-2/1A
Tensile Stress (Yield)	9570	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	8.0	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	399000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.1	ft-lb/in ²	ISO 179/1eA
Notched Izod Impact Strength (73°F)	2.3	ft-lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	216	°F	ISO 75-2/A
Vicat Softening Temperature	322	°F	ISO 306/B50
Melting Temperature ²	333	°F	ISO 11357-3
Melting Temperature	329	°F	
CLTE - Flow	6.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.7E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr

Celcon® M270UV

Celanese Corporation - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F
Nozzle Temperature	374 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 580	psi

Injection Notes

Zone4 temperature: 190 to 200°C
Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min