



Celcon® M90-45H

Celanese Corporation - Acetal (POM) Copolymer

Saturday, November 2, 2019

General Information

Product Description

Celcon® M90-45H is an acetal copolymer which has been stabilized to give protection against property and color degradation in interior applications where UV exposure is anticipated. Celcon® M90-45H is formulated in custom colors for Toyota interior UV stabilized applications

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• UV Resistant	• UV Stabilized	
Uses	• Automotive Applications	• Automotive Interior Parts	
RoHS Compliance	• Contact Manufacturer		
Appearance	• Colors Available		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.7	%	
Flow	1.9	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	399000	psi	ISO 527-2/1A
Tensile Stress (Yield)	9140	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	10	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	361000	psi	ISO 178
Compressive Stress			ISO 604
1% Strain	3480	psi	
6% Strain	12200	psi	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	1.9	ft·lb/in ²	
73°F	2.9	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	196	°F	ISO 75-2/A
Vicat Softening Temperature	322	°F	ISO 306/B50
Melting Temperature ²	331	°F	ISO 11357-3
Melting Temperature	331	°F	
CLTE - Flow	6.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.7E-5	in/in/°F	ISO 11359-2

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Celcon® M90-45H

Celanese Corporation - Acetal (POM) Copolymer

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F
Nozzle Temperature	356 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 580	psi

Injection Notes

Zone4 temperature: 180 to 200°C
Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min