



Celcon® WR25Z

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Celcon® WR25Z is a 2.5 nominal melt flow rate based acetal copolymer stabilized to provide maximum ultraviolet radiation resistance in outdoor applications. Celcon® WR25Z is a lower flow product providing improved toughness. Available in black only.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Toughness	• Low Flow	• UV Resistant
Uses	• Outdoor Applications		
RoHS Compliance	• Contact Manufacturer		
Appearance	• Black		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.10	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	1.6	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	377000	psi	ISO 527-2/1A
Tensile Stress (Yield)	8850	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	10	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	370000	psi	ISO 178
Flexural Stress (3.5% Strain)	9720	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.0	ft-lb/in ²	ISO 179/1eA
Notched Izod Impact Strength (73°F)	3.0	ft-lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	198	°F	ISO 75-2/A
Vicat Softening Temperature	322	°F	ISO 306/B50
Melting Temperature ²	331	°F	ISO 11357-3
Melting Temperature	329	°F	
CLTE - Flow	5.6E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.1E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F

Celcon® WR25Z

Celanese Corporation - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Nozzle Temperature	374 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow	
Back Pressure	< 580	psi

Injection Notes

Zone4 temperature: 190 to 200°C
Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min