



Celcon® WR90Z

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Celcon® WR90Z is a standard nominal 9 melt flow rate based acetal copolymer stabilized to provide maximum ultraviolet radiation resistance in outdoor applications while retaining a good balance of properties. Available in black only.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• UV Resistant		
Uses	• Outdoor Applications		
RoHS Compliance	• Contact Manufacturer		
Appearance	• Black		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.6	%	
Flow	1.7	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	384000	psi	ISO 527-2/1A
Tensile Stress (Yield)	9140	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	8.0	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	370000	psi	ISO 178
Flexural Stress (3.5% Strain)	10200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.6	ft-lb/in ²	
73°F	2.6	ft-lb/in ²	
Charpy Unnotched Impact Strength (73°F)	47	ft-lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	2.6	ft-lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	306	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	203	°F	ISO 75-2/A
Vicat Softening Temperature	322	°F	ISO 306/B50
Melting Temperature ²	331	°F	ISO 11357-3
Melting Temperature	331	°F	
CLTE - Flow	5.6E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.1E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F

Celcon® WR90Z

Celanese Corporation - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F
Nozzle Temperature	374 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 580	psi

Injection Notes

Zone4 temperature: 190 to 200°C
Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min